

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup> : A61L 27/00, 31/00, 29/00		A1	(11) International Publication Number: WO 94/27651
			(43) International Publication Date: 8 December 1994 (08.12.94)
(21) International Application Number: PCT/IB94/00083		(81) Designated States: AU, CA, DE, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 26 April 1994 (26.04.94)			
(30) Priority Data: 08/070,074 1 June 1993 (01.06.93) US		Published With international search report.	
(71) Applicant: HOWMEDICA INC. [US/US]; 235 East 42nd Street, New York, NY 10017 (US).			
(72) Inventors: SUN, Deh-Chuan; 97 Woodstone Road, Rockaway, NJ 07866 (US). STARK, Casper, F.; 2 Cambridge Road, Pompton Lakes, NJ 07442 (US).			
(74) Agents: SPIEGEL, Allen, J. et al.; Pfizer Inc., Patent Dept., 235 East 42nd Street, New York, NY 10017 (US).			
(54) Title: NON-OXIDIZING POLYMERIC MEDICAL IMPLANT			
(57) Abstract			
<p>A medical implant made of polymeric material having an increased oxidation resistance is formed by a method including the steps of placing a resin powder in a sealed container. A substantial portion of the oxygen is removed from the sealed container by either a vacuum, an oxygen absorbent or by flushing with inert gas. The container is then repressurized with a gas such as nitrogen, argon, helium or neon so that long term storage may be possible. On use, the resin is transferred to a forming device which both melts and forms the resin in an oxygen reduced atmosphere to produce a polymeric raw material such as a rod or bar stock. The medical implant is then formed from this raw material annealed and sealed in an airtight package in an oxygen reduced atmosphere. The implant is then radiation sterilized and thereafter annealed in the package for a predetermined time and temperature sufficient to form cross-links between any free radicals in neighboring polymeric chains.</p>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

NON-OXIDIZING POLYMERIC MEDICAL IMPLANTBACKGROUND OF THE INVENTIONField of the Invention

- 5           This invention relates to medical implants formed of a polymeric material such as ultra-high molecular weight polyethylene, with superior oxidation resistance upon irradiation and a method for making the same.

Description of the Prior Art

- 10           Various polymer systems have been used for the preparation of artificial prostheses for biomedical use, particularly orthopedic applications. Among them, ultra-high molecular weight polyethylene is widely used for articulation surfaces in artificial knee and hip replacements. Ultra-high molecular weight polyethylene (UHMWPE) has been defined as those linear polyethylenes which have a relative  
15           viscosity of 2.3 or greater at a solution concentration of 0.05% at 135°C in decahydronaphthalene. The nominal weight - average molecular weight is at least 400,000 and up to 10,000,000 and usually from three to six million. The manufacturing process begins with the polymer being supplied as fine powder which is consolidated into various forms, such as rods and slabs, using ram extrusion or  
20           compression molding. Afterwards, the consolidated rods or slabs are machined into the final shape of the orthopedic implant components. Alternatively, the component can be produced by compression molding of the UHMWPE resin powder.

- All components must then go through a sterilization procedure prior to use, but usually after being packaged. There exists several sterilization methods which  
25           can be utilized for medical applications, such as the use of ethylene oxide, heat, or radiation. However, applying heat to a packaged polymeric medical product can destroy either the integrity of the packaging material (particularly the seal, which prevents bacteria from going into the package after the sterilization step) or the product itself.

- 30           Because ethylene oxide may adversely impact environmental and employee safety, gamma ray, x-ray or electron beam radiation has been utilized as a preferred means of sterilization. These types of radiation use a high energy beam to kill

-2-

bacteria, viruses, or other microbial species contained in the packaged medical products, achieving the goal of product sterility.

However, it has been recognized that regardless of the radiation type, the high energy beam causes generation of free radicals in polymers during radiation. It has also been recognized that the amount of free radicals generated is dependent upon the radiation dose received by the polymers and that the distribution of free radicals in the polymeric implant depends upon the geometry of the component, the type of polymer, the dose rate, and the type of radiation beam. The generation of free radicals can be described by the following reaction (which uses polyolefin and gamma ray irradiation for illustration):








\* (through C-C chain scission or C-H scission)

Depending whether or not oxygen is present, primary free radicals  $\text{r}\cdot$  will react with oxygen and the polymer according to the following reactions as described in "Radiation Effects on Polymers", edited by Roger L. Clough and Shalaby W.

Shalaby, published by American Chemical Society, Washington, D.C., 1991.

In the presence of oxygen




In radiation in air, primary free radicals  $r\cdot$  will react with oxygen to form peroxy free radicals  $rO_2\cdot$ , which then react with polyolefin (such as UHMWPE) to start the oxidative chain scission reactions (reactions 2 through 6). Through these reactions, material properties of the plastic, such as molecular weight, tensile, and wear properties, are degraded.

Recently, it was found that the hydroperoxides ( $rOOH$  and  $POOH$ ) formed in reactions 3 and 5 will slowly break down as shown in reaction 7 to initiate post-radiation degradation. Reactions 8 and 9 represent termination steps of free radicals to form ester or carbon-carbon cross-links. Depending on the type of polymer, the extent of reaction 8 and 9 in relation to reactions 2 through 7 may vary. For irradiated UHMWPE, a value of 0.3 for the ratio of chain scission to cross-linking has been obtained, indicating that even though cross-linking is a dominant mechanism, a significant amount of chain scission occurs in irradiated polyethylene.

By applying radiation in an inert atmosphere, since there is no oxidant present, the primary free radicals  $r\cdot$  or secondary free radicals  $P\cdot$  can only react with other neighboring free radicals to form carbon-carbon cross-links, according to reactions 10 through 12 below. If all the free radicals react through reactions 10 through 12, there will be no chain scission and there will be no molecular weight degradation. Furthermore, the extent of cross-linking is increased over the original polymer prior to irradiation. On the other hand, if not all the free radicals formed are combined through reactions 10, 11 and 12, then some free radicals will remain in the plastic component.

In an Inert Atmosphere



It is recognized that the fewer the free radicals, the better the polymer retains its physical properties over time. The greater the number of free radicals, the greater the degree of molecular weight and polymer property degradation will occur.

-4-

Applicant has discovered that the extent of completion of free radical cross-linking reactions is dependent on the reaction rates and the time period given for reaction to occur.

Several prior art patents attempt to provide methods which enhance  
5 UHMWPE physical properties. European Patent Application 0 177 522 B1 discloses UHMWPE powders being heated and compressed into a homogeneously melted crystallized morphology with no grain memory of the UHMWPE powder particles and with enhanced modulus and strength. U.S. Patent 5,037,928 discloses a prescribed heating and cooling process for preparing a UHMWPE exhibiting a combination of  
10 properties including a creep resistance of less than 1% (under exposure to a temperature of 23°C and a relative humidity of 50% for 24 hours under a compression of 1000 psi) without sacrificing tensile and flexural properties. U.K. Patent Application GB 2 180 815 A discloses a packaging method where a medical device which is sealed in a sterile bag, after radiation/sterilization, is hermetically sealed in a  
15 wrapping member of oxygen-impermeable material together with a deoxidizing agent for prevention of post-irradiation oxidation.

U.S. Patent 5,153,039 relates to a high density polyethylene article with oxygen barrier properties. U.S. Patent 5,160,464 relates to a vacuum polymer irradiation process.

20

#### SUMMARY OF THE INVENTION

The present invention relates to a method for providing a polymeric material, such as UHMWPE, with superior oxidation resistance upon irradiation. For the purpose of illustration, UHMWPE will be used as an example to describe the  
25 invention. However, all the theories and processes described hereafter should also apply to other polymeric materials such as polypropylene, high density polyethylene, polyester, nylon, polyurethane and poly(methylmethacrylate) unless otherwise stated.

As stated above, while UHMWPE polymer is very stable and has very good resistance to aggressive media except for strong oxidizing acids. Upon sterilization  
30 radiation, free radicals are formed which cause UHMWPE to become activated for chemical reactions and physical changes. Possible chemical reactions include reacting with oxygen, water, body fluids, and other chemical compounds while physical changes include density, crystallinity, color, and other physical properties. In the present invention a new sterilization radiation process greatly reduces the

adverse effects caused by a conventional radiation process. Furthermore, this new sterilization process does not employ stabilizers, antioxidants, or any other chemical compounds which may have potential adverse effects in biomedical or orthopedic applications.

5 In the sterilization process of the present invention, a polymeric orthopedic implant component to be sterilized by radiation does not contain oxidants, such as oxygen or water (or moisture), or free radicals. This may be accomplished by obtaining a raw material for the implant manufactured under a special process as described herein and forming a part of the invention.

10 The finished polymeric orthopedic component is then sealed in an oxidant-free atmosphere. This oxidant-free atmosphere is maintained during radiation. The radiated polymeric component is then subjected to a heat treatment to cross-link all the free radicals within themselves. During this treatment, the condition of oxidant-free atmosphere is maintained. The irradiated, heat treated plastic component is  
15 now ready to use. Exposure to oxygen or moisture will not cause oxidation. The oxidation resistance to any oxidizing agent is similar to that of the unirradiated virgin polymer.

It is therefore an object of the invention to provide a polymeric orthopedic implant having superior oxidation resistance after irradiation.

20 It is still another object of the invention to provide a method for manufacturing such an implant from the resin powder thereof through the final sterilization step so that the implant may thereafter be exposed to air without degradation due to oxidation.

These and other objects are achieved by a method for producing a polymeric  
25 medical implant including the steps of placing the polymeric resin in a sealed container and removing a substantial portion of the oxygen from the container. After a predetermined time, the container is repressurized with an inert gas such as nitrogen, argon, helium or neon. The resin is thereafter transferred to a forming device which normally melts and forms the resin in an oxygen reduced atmosphere  
30 to produce a polymeric raw material. The polymeric raw material, such as UHMWPE is then machined to an implant such as a tibial tray or a liner for an acetabular cup. The finished part is then sealed into a package in an oxygen reduced atmosphere. The package is of an air-tight nature to prevent oxygen or moisture from entering after the package is sealed. The then packaged implant is radiation sterilized and

then heat treated for the predetermined time and temperature sufficient to form cross-links between free radicals of the neighboring polymeric chains. This prevents further oxidation once the implant is removed from the package.

In general, the implant is heated for at least 48 hours at a temperature of  
5 about 37°C to about 70°C and preferably for 144 hours at 50°C.

#### DESCRIPTION OF THE PREFERRED EMBODIMENT

In the preferred method, a raw polymeric material such as UHMWPE is obtained by, for example, ram extrusion, compression molding, or other forming  
10 processes. These methods use virgin polymer powder as a starting material. However, virgin polymer resin powder may contain air or moisture, which may exist in the resin micro-structure or simply deposited on the resin surfaces. If air or moisture is not removed from resin powder prior to the forming process, it can be trapped in the plastic matrix after forming and can not escape. This is true even with  
15 the use of vacuum or gas flushing techniques. During the sterilization radiation process, the trapped air or moisture or both will react with free radicals generated in the plastic to cause oxidation. The trapped moisture can also absorb radiation energy and dissociate into oxygen and hydroxyl free radicals which will also react with the plastic to cause oxidation. Therefore, by removing air and moisture prior to  
20 the forming process, oxidation during sterilization radiation can be avoided.

The preferred method for eliminating air and moisture is to apply a vacuum of less than 3" of mercury (76 torr) to the polymer resin for a prescribed time to reduce the levels of air and moisture to a minimal or acceptable value. The level for oxygen is preferably 0.5% (volume by volume and no more than 1%). The moisture level is  
25 preferably 10% of relative humidity (and no more than 20% relative humidity). Then sufficient amounts of deoxidizing agents, such as oxygen absorbents and moisture desiccants, are placed together with the polymer resin in a sealed container to reduce the levels of air and moisture to the minimal or acceptable value. An example of an oxygen absorbent is AGELESS® which is an iron oxide compound  
30 and commercially available from Cryovac Division, W.R. Grace & Co., Duncan, S.C.. An example of moisture desiccant is silica gel which is commercially available. These materials are placed with the resin in the sealed container for approximately 10 hours. Alternately, or in combination, an inert gas, such as nitrogen, argon, helium or neon is used to flush the container, holding the polymer resin powder,



until the levels of air and moisture are reduced to the accepted value. Of course, any combination of the above methods can also be used.

In order to ensure a raw material for an orthopedic implant with no oxygen, not only must the UHMWPE resin powder be free of air and moisture, but the entire forming operation of, for example, ram extrusion, compression molding, or other forming process should be carried out in an inert or low oxygen atmosphere as well. During the forming process, due to high temperature and high pressure applied in the process, UHMWPE polymer chains may be broken to generate free radicals and cross-links. While cross-links generated in the forming process have no adverse effects on material properties, the free radicals produced, as described above, can react with air or other oxidants. Therefore, it is important to maintain the inert atmosphere during the forming process to minimize oxidation.

Any free radicals generated should be eliminated as soon as the forming process is completed by annealing. If the formed UHMWPE contains free radicals and is exposed to air or other oxidants after the forming process, oxidation will occur. The polymer should be annealed at an elevated temperature in an inert atmosphere for a prescribed time. This is because the rate of free radical reactions (reactions 10 through 12) increase with increasing temperature, according to the following general expressions:

$$\frac{dr\cdot}{dt} = k_1 [r\cdot] \quad \text{and} \quad \frac{dP\cdot}{dt} = k_2 [P\cdot] \quad (13)$$

Compared to room temperature, an elevated temperature not only increases the reaction rate constants,  $k_1$  and  $k_2$ , but also helps free radicals  $r\cdot$  and  $P\cdot$  to migrate in the plastic matrix to meet other neighboring free radicals for cross-linking reactions. In general, the desired elevated temperature is between the room temperature and the melting point of the polymer. For UHMWPE, this temperature range is between about 25°C and about 140°C. However, the preferred annealing temperature range is from about 37°C to about 135°C. The preferred time and temperature is 130°C for 20 hours with the minimum annealing time being about 4 hours (requiring a temperature at the high end of the range). It is to be noted that the higher the temperature used, the shorter the time period needed to combine free radicals. Additionally, due to the high viscosity of an UHMWPE melt, the formed UHMWPE often contains residual (internal) stress caused by incomplete relaxation

during the cooling process, which is the last step of the forming process. The annealing process described herein will also help to eliminate or reduce the residual stress. A residual stress contained in a plastic matrix can cause dimensional instability and is in general undesirable.

- 5           In applications such as for orthopedic implants, the formed UHMWPE is further machined into desired shapes. In general, the machining is done at room temperature and no damage to the plastic will occur. However, certain machine tools, when operated at a high speed, may generate local heat and cause thermal breakdown of UHMWPE polymer chains. In this case, the above described
- 10   annealing process may be employed to eliminate any newly formed free radicals prior to packaging.

- After machining, the polymeric component is packaged in an air tight package in an oxidant-free atmosphere. Thus, all air and moisture must be removed from the package prior to the sealing step. Machines to accomplish this are
- 15   commercially available, such as from Orics Industries Inc., College Point, New York, which flush the package with a chosen inert gas, vacuum the container, flush the container for the second time, and then heat seal the container with a lid. In general, less than 0.5% (volume by volume) oxygen concentration can be obtained consistently. An example of a suitable oxidant impermeable (air tight) packaging
- 20   material is polyethylene terephthalate (PET). Other examples of oxidant impermeable packaging material is poly(ethylene vinyl alcohol) and aluminum foil, whose oxygen and water vapor transmission rates are essentially zero. All these materials are commercially available. Several other suitable commercial packaging materials utilize a layer structure to form a composite material with superior oxygen and
- 25   moisture barrier properties. An example of this type is a layered composite comprised of poly-propylene/poly(ethylene vinyl alcohol)/polypropylene.

- In general, the sterilization radiation step for the packaged implant may take a few hours to complete. As described above, it is imperative that during this time period, the transmission of oxidants, such as oxygen and moisture, into the package
- 30   be kept to a minimal or at an acceptable value to avoid oxidation.

          Following sterilization radiation, a heat treatment step should be performed in an inert atmosphere and at an elevated temperature to cause free radicals to form cross-links without oxidation. If proper packaging materials and processes are used and oxidant transmission rates are minimal, then the oxidant-free atmosphere can be

maintained in the package and a regular oven with air circulation can be used for heat treatment after sterilization. To absolutely ensure that no oxidants leak into the package, the oven may be operated under a vacuum or purged with an inert gas. In general, if a higher temperature is used, a shorter time period is required to

5 achieve a prescribed level of oxidation resistance and cross-linking. In many cases, the relationship between the reaction temperature and the reaction rate follows the well-known Arrhenius equation:

$$k_1 \text{ or } k_2 = A * \exp (\Delta H/T) \quad (14)$$

10

where  $k_1$  and  $k_2$  are reaction rate constants from reactions 13 and 14  
 A is a reaction dependent constant  
 $\Delta H$  is activation energy of reaction  
 T is absolute temperature (K)

15

However, the temperature should not exceed the distortion temperature of either the packaging material or the plastic components. For UHMWPE, the temperature range is between about 25°C and about 140°C. However, considering the distortion of the packaging material, the preferred temperature is 37°C to 70°C.

20

It is very important to ensure that the number of free radicals has been reduced to a minimal or an accepted level by the heat treatment. This is because the presence of an oxidant causes not only the oxidation of pre-existing free radicals, but also the formation of new free radicals via reactions 2 through 7. When the number of free radicals grows, the extent of oxidation and the oxidation rate will

25

increase according to the following equations:

$$\frac{dr\cdot}{dt} = k_3 [r\cdot][O_2] \quad \text{and} \quad \frac{dP\cdot}{dt} = k_4 [P\cdot][O_2] \quad (15)$$

30

Where free radicals  $r\cdot$  and  $P\cdot$  can grow in number in the presence of oxidants and in turn increase the oxidation rates. It is also to be noted that the oxidation reaction rate constants  $k_3$  and  $k_4$  increase with increasing temperature, similar to  $k_1$  and  $k_2$ . Therefore, to determine if a certain level of residual free radicals is acceptable or not, it is required to evaluate specific material properties after the

35 plastic sample is stored or aged at the application temperature for a time period which is equal to or longer than the time period intended for the application of the

plastic component. An alternative to the method to assess the aging effect is to raise the aging temperature of the plastic sample for a shorter time period. This will increase the reaction rate constants  $k_3$  and  $k_4$  significantly and shorten the aging time. It has been found that an acceptable level of residual free radicals is

5  $1.0 \times 10^{17}/g$  for UHMWPE use for orthopedic implants.

After heat treatment, the irradiated packaged plastic component is now ready to use. The package can be opened and exposed to air or moisture without causing oxidation. The oxidation resistance of the sterilized plastic component to other oxidants is similar to that of the virgin, unirradiated polymer.

10

#### Sample Preparation

A surgical grade UHMWPE rod produced by ram extrusion was machined into samples of desirable shapes. Four sets of samples were prepared using these machined samples by the following methods:

15 Method A: an UHMWPE sample as machined and unirradiated

Method B: An UHMWPE sample was heat sealed in a glycol-modified polyethylene terephthalate (PETG, made by Eastman Plastics, Inc., Kingsport, Tennessee) blister in air with an aluminum lid of 0.1 mm in thickness. The sealed blister containing the UHMWPE sheet was  
20 sterilized by irradiation of gamma-rays in a dose of 2.5 Mrad. The package was then opened and exposed to room air.

Method C: An UHMWPE sample was placed in a PETG blister and heat sealed in dry nitrogen with an aluminum lid of 0.1 mm in thickness by the Orics Vacuum Gas Flush Heat Seal Machine (Model SLS-VGF-100M for  
25 modified atmosphere packaging, made by Orics Industries Inc., College Point, New York.) which went through the following cycles:

- 30
- i) nitrogen gas (moisture-free) flush for five seconds
  - ii) vacuum to a pressure of equal to or below 3 inches of mercury
  - iii) nitrogen gas flush (moisture-free) for five seconds
  - iv) heat seal

The oxygen concentration in the sealed blister was measured by a Mocon Oxygen Analyzer to be 0.325% (volume by volume). The

5 sealed blister containing the UHMWPE sample was sterilized by irradiation of gamma-rays in a dose of 2.5 Mrad. The oxygen concentration in the sealed blister after sterilization radiation was measured to be 0.350%. The package was then opened and exposed to room air.

Method D: Same as Method C, except that after gamma-ray irradiation, the sealed blister containing the UHMWPE sample was heat treated at 50°C for 144 hours in an oven, then transferred from the oven to room temperature for cooling. After the package was cooled to room temperature, the oxygen concentration was measured by a Mocon Oxygen Analyzer to be 0.360%. The package was then opened and exposed to room air.

15 Samples prepared by the above methods were used in the following examples for evaluation.

Example 1:

Two sets of 1-mm-thick UHMWPE sheets prepared by Methods A through D above were oven aged in air at 80°C for 11 and 23 days respectively. After these sheets were cooled in room temperature, a thin film specimen of about 100 microns in thickness was cut from each of the 1-mm-thick aged UHMWPE sheets and placed in an IR window for a standard FTIR (A Nicolet 710 FTIR system was used) transmission run. A total of 32 spectra (scans) were collected and averaged. To determine the extent of oxidation, the IR absorption peaks in the frequency range of between 1660 and 1800  $\text{cm}^{-1}$ , corresponding to carbonyl (C=O) functional groups, were integrated for the peak area. The peak area is proportional to the amount of oxidized UHMWPE in the specimen. To correct for difference in specimen thickness, the integrated peak area was then normalized to the specimen thickness, by dividing by the area of the 1463  $\text{cm}^{-1}$  (methyl) peak which is proportional to the specimen thickness. The obtained ratio was defined as oxidation index. A third set of 1-mm-thick UHMWPE sheets prepared by methods A through D, but without oven aging, were also evaluated by the same FTIR method for comparison. Oxidation indices obtained are shown in Table 1:

TABLE 1

	Sample	Oxidation Index
5	Method A / not oven aged	ca. 0.
	Method A / 11 day oven aging	ca. 0.
	Method A / 23 day oven aging	ca. 0.
10	Method B / not oven aged	0.02
	Method B / 11 day oven aging	0.06
	Method B / 23 day oven aging	0.11
15	Method C / not oven aged	0.01
	Method C / 11 day oven aging	0.04
	Method C / 23 day oven aging	0.08
20	Method D / not oven aged	0.01
	Method D / 11 day oven aging	0.01
	Method D / 23 day oven aging	0.01

From Table 1 results, it can be seen that the unirradiated UHMWPE sample (Method A) was free of oxidation (below the FTIR detectable level), even after 23 days of oven aging in air at 80°C. On the other hand, the UHMWPE sample irradiated in air (Method B) showed considerable oxidation and the extent of oxidation (as indicated by the oxidation index) increased with increasing aging time. After 23 days of oven aging, the oxidation index reached 0.11. For the UHMWPE sample irradiated in nitrogen (Method C), the initial oxidation index before oven aging was 0.01 which was not significant. However, during the oven aging, the oxidation index increased to 0.04 for 11 days and 0.08 for 23 days respectively. The results indicate that while irradiation in an inert atmosphere is an improvement over oxidation in air, the irradiated plastic component will oxidize further over time once it is exposed to air or other oxidants. In contrast, the UHMWPE sample irradiated in nitrogen followed by heat treatment at 50°C for 144 hours (Method D), showed an

initial oxidation index of only 0.01 which did not increase after 11 or 23 days of oven aging, indicating that this sample has superior oxidation resistance than the samples prepared by Method B or C.

5 Example 2:

Two sets of 1-mm-thick UHMWPE sheets prepared by Methods B through D cited in the Sample Preparation were oven aged in air at 80°C for 11 and 23 days respectively. After these sheets were cooled in room temperature, six tensile specimens with a dumbbell shape according to ASTM D638 (Type IV) were cut from each of the 1-mm-thick aged UHMWPE sheets. A standard tensile test was performed for each specimens at a speed of 2 inches/min. Another set of 1-mm-thick UHMWPE sheets prepared by Methods B through D cited in the Sample Preparation, but without oven aging, were also evaluated by the same tensile test method for comparison. Tensile breaking strength results (average of six tests for each condition) are shown in Table 2:

TABLE 2

	Sample	Tensile Breaking Strength, psi
20	Method B / not oven aged	6510
	Method B / 11 day oven aging	5227
	Method B / 23 day oven aging	3192
	Method C / not oven aged	6875
25	Method C / 11 day oven aging	6400
	Method C / 23 day oven aging	6004
	Method D / not oven aged	6941
	Method D / 11 day oven aging	7113
30	Method D / 23 day oven aging	6904

From Table 2, tensile breaking strength shows the most deterioration for the sample irradiated in air (Method B). The sample irradiated in nitrogen (Method C) shows some improvement over the sample prepared by Method B. However, the decrease in tensile breaking strength upon oven aging still occurs. In contrast, the sample irradiated in nitrogen followed by heat treatment (50°C for 144 hours, Method D), shows no change in tensile breaking strength, indicating a superior oxidation resistance.

### Example 3:

Two sets of 1-mm-thick UHMWPE sheets prepared by Methods B and Method D cited in the Sample Preparation were oven aged in air at 80°C for 11 and 23 days respectively. After these sheets were cooled in room temperature, samples cut from sheets were characterized by a high temperature gel permeation chromatograph (GPC) column for molecular weight distribution. The samples were dissolved in hot trichlorobenzene (TCB). They were then run in the aforementioned solvent at 1.2 ml/min. using a Jordi Gel Mixed Bed Column, 50cm x 10.0mm ID., at a column oven temperature of 145°C on the Waters 150C Chromatograph. The injection size was 250uL of a 0.1% solution. An antioxidant (N-phenyl-2-naphthylamine) was added to all high temperature GPC samples to prevent polymer deterioration.

Prior to sample runs, the column was calibrated using narrow MW polystyrene standards. Since the samples were only partially soluble in the solvent due to cross-linking, the so-determined molecular weight distribution was for the soluble portion only. To determine the extent of cross-linking (solubility), a two hundred milligram sample cut from sheets were dissolved in 100cc of 1,2,4-trichlorobenzene. Each sample was then heated to approximately 170°C with N-phenyl-2-naphthylamine antioxidant added for 6 hours. The samples were then hot filtered at approximately 170°C using separate preweighed high temperature filters for each sample.

After filtration, the filters were cooled to room temperature and washed individually with dichloromethane. They were then placed in a convection oven at 105°C for 6 hours to dry and then reweighed. The weight fraction of the undissolved (cross-linked) portion was then determined based upon the initial weight of 200 mg. To determine the low molecular weight fraction present in each sample, the weight fraction of molecular weight below  $10^5$  in the soluble portion, determined by GPC,



was multiplied by the percent solubility to give weight percent of low molecular weight fraction in each sample. Results are shown in Table 3:

TABLE 3

Sample	Weight Percent of Soluble Portion Below $10^5$	Percent Solubility in Solvent	Weight Percent of Entire Sample Below $10^5$
Method B /without oven aging	28.0	98.2	27.5
Method B /11 day oven aging	36.2	100.0	36.2
Method B /23 day oven aging	48.1	100.0	48.1
Method D /without oven aging	22.7	80.9	18.4
Method D /11 day oven aging	20.5	73.6	15.1
Method D /23 day oven aging	24.2	74.7	18.1

From Table 3, it can be seen that the sample made by Method D contains more cross-linking (i.e. less soluble) than one made by Method B. Upon oven aging, the low molecular weight fraction (defined as below  $10^5$ ) in the sample made by Method B increases from 0.275 to 0.481 while that of the sample made by Method D remains virtually unchanged at about 0.18 after 23 days of oven aging.

The increase in low molecular weight fraction was due to chain scission caused by oxidative reactions. The results indicate that the process of method D can produce an irradiated polymer with a superior oxidation resistance.

Example 4:

UHMWPE samples of 0.5 inch cubes prepared by Methods B and Method D cited in the Sample Preparation were evaluated for deformation under load (creep resistance). Testing procedures according to ASTM D 621 (A) (24hr/23°C/1000 psi/90 min recovery) were used. Results are summarized in Table 4:

TABLE 4

Sample	Deformation under Load, %
Method B	0.80
Method D	0.60

10

From Table 4, it is concluded that the sample prepared by Method D, the invention, possesses a superior creep resistance (0.6%) to one prepared by Method B (0.8%).

15

Example 5:

Two 1-mm-thick UHMWPE samples were annealed in a oven filled with air and dry nitrogen (oxygen concentration is below 0.2%) respectively at 130°C for 20 hours in order to remove residual stress on the samples. After the sheets were cooled to room temperature in the oven, they were removed from the oven and cut into dumbbell shaped tensile specimens (ASTM D 638, Type V) for evaluation. A standard tensile test according to ASTM D 638 was performed at a speed of 2 inches/min for each of six specimens annealed in air and in dry nitrogen respectively. Results are shown in Table 5:

20

25

TABLE 5

Sample	EAB, %	TYS, psi	TBS, psi	Toughness, lbs-in/in <sup>3</sup>
Air annealed	414	3547	6257	10,210
Nitrogen annealed	485	3517	8917	18,960

30

Note: EAB - elongation at break  
TYS - tensile yield strength  
TBS - Tensile breaking strength

35

From the above table, it is seen that the sample annealed in nitrogen exhibits a higher elongation at break, a higher tensile breaking strength, and a higher toughness, compared to one annealed in air, while the tensile yield strength is similar between the two samples. The results indicate that the sample annealed in nitrogen is more ductile than the one annealed in air. The loss of ductility in the sample annealed in air is due to oxidative chain scission.

To determine oxidation indices in these two samples, a thin film specimen of ca. 100 microns in thickness was cut from each of the 1-mm-thick annealed UHMWPE sheets and placed in an IR window for a standard FTIR (a Nicolet 710 FTIR system was used) transmission run, using the procedures and calculations employed in the Sample Preparation. Oxidation indices obtained are shown in Table 6.

TABLE 6

Sample	Oxidation Index
Air Annealed	0.10
Nitrogen Annealed	ca. 0.0

From the above results, it is seen that the UHMWPE sample annealed in air after ram extrusion showed significant oxidation due to free radicals generated in the forming process. In contrast, the UHMWPE sample annealed in nitrogen showed no oxidation (below the FTIR detectable level). It is concluded that annealing in nitrogen can prevent the polymer from oxidation and produce a polymer with superior ductility.

While several examples of the present invention have been described, it is obvious that many changes and modifications may be made thereunto, without departing from the spirit and scope of the invention.

CLAIMS:

1. A method for producing a polymeric medical implant material having improved oxidation resistance comprising the steps of:  
forming the implant from the polymeric material;  
5 sealing the formed implant in a package in an oxygen reduced atmosphere;  
radiation sterilizing said packaged implant; and  
heating said packaged implant for a predetermined time and temperature sufficient to form cross-links between free radicals in neighboring polymeric chains.
2. The method for producing an implant set forth in claim 1 wherein said  
10 predetermined temperature is between about 37°C and about 70°C.
3. The method for producing an implant as set forth in claim 2 wherein said predetermined time is at least forty eight hours.
4. The method for producing an implant as set forth in claim 3 wherein said predetermined temperature is 50°C and said predetermined time is 144 hours.
- 15 5. The method for producing an implant as set forth in claim 1 wherein the polymeric material is ultra high molecular weight polyethylene having a molecular weight between 400,000 and 10,000,000.
6. The method for producing an implant as set forth in claim 5 wherein said predetermined temperature is 50°C and said predetermined time is 144 hours.
- 20 7. The method for producing an implant as set forth in claim 1 wherein said radiation sterilization is performed by gamma, x-ray or electron beam radiation.
8. The method as set forth in claim 1 wherein said oxygen reduced atmosphere has no more than 1% oxygen.
9. The method for producing an implant as set forth in claim 8 wherein  
25 said oxygen reduced atmosphere is made up of a gas selected from the group consisting of nitrogen, helium, argon, and neon and a combination thereof.
10. The method for producing an implant as set forth in claim 8 wherein said reduced oxygen atmosphere is produced by a vacuum of less than 3 inches of mercury.
- 30 11. The method for producing an implant as set forth in claim 8 wherein said sealing in a reduced oxygen atmosphere is produced by first flushing said package with a gas selected from the group consisting of nitrogen, helium, argon and neon and a combination thereof, followed by applying a vacuum of less than 3

inches of mercury to said package, followed by flushing said package with a gas selected from said group and a combination thereof.

12. A medical implant made of a polymeric material comprising polymeric chains having a free radical concentration of less than  $1 \times 10^{17}/g$  achieved by  
5 heating said implant to a temperature of between about 37°C and about 70°C for at least forty-eight hours in an oxygen reduced atmosphere prior to the oxidation of said free radicals.

13. The medical implant as set forth in claim 12 wherein said polymeric material is polyethylene having a molecular weight of between 400,000 and  
10 10,000,000.

14. A method for producing raw polymeric material having improved oxidation resistance from a plastic resin powder for a medical implant comprising the steps of:

placing the resin in a sealed container;  
15 removing a substantial portion of the oxygen from said sealed container;  
repressurizing the sealed container with a gas selected from the group consisting of nitrogen, argon, helium and neon and a combination thereof;  
then transferring said resin to a forming device which both melts and forms said resin in an oxygen reduced atmosphere to produce the raw material; and  
20 thereafter annealing the raw material for a predetermined time at a predetermined temperature.

15. The method as set forth in claim 14 wherein the oxygen content of the atmosphere in said sealed container is reduced to less than 1%.

16. The method as set forth in claim 15 wherein said forming device  
25 operates in an atmosphere of less than 1% oxygen.

17. The method as set forth in claim 14 wherein the resin material is polyethylene having a molecular weight of between 400,000 and 10,000,000.

18. The method for producing a raw material as set forth in claim 14 wherein said removal of said oxygen from said container is a method selected from  
30 the group consisting of applying a vacuum, flushing with an inert gas and using an oxygen absorbent and a combination thereof.

19. The method for producing a raw material as set forth in claim 14 wherein said annealing step takes place at a temperature between about 37°C and about 135°C for at least four hours in an oxygen reduced atmosphere.

20. A method for producing a medical implant from a plastic resin powder, the implant having improved oxidation resistance comprising the steps of:
- placing the resin in a sealed container;
  - removing a substantial portion of the oxygen from said sealed container;
  - 5 repressurizing the sealed container with a gas selected from the group consisting of nitrogen, argon, helium and neon and a combination thereof;
  - then transferring said resin to a forming device which both melts and forms said resin in an oxygen reduced atmosphere to produce a polymeric raw material;
  - thereafter annealing the raw material for a predetermined time at a prede-
  - 10 termined temperature;
  - forming the implant from the polymeric raw material;
  - sealing the formed implant in a package in an oxygen reduced atmosphere;
  - radiation sterilizing said packaged implant; and
  - heating said packaged implant for a predetermined time and temperature
  - 15 sufficient to form cross-links between free radicals in neighboring polymeric chains.
21. The method for producing a raw material as set forth in claim 20 wherein said removal of said oxygen from said container is a method selected from the group consisting of applying a vacuum, flushing with an inert gas and using an oxygen absorbent and a combination thereof.
22. The method for producing a raw material as set forth in claim 20 wherein said annealing step takes place at a temperature between about 37°C and about 135°C for at least four hours in an oxygen reduced atmosphere.
23. A method for producing a polymeric medical implant material having improved oxidation resistance comprising the steps of:
- 25 forming the implant from the polymeric material;
  - packaging the formed implant in an oxygen reduced atmosphere;
  - radiation sterilizing said packaged implant while maintaining said oxygen reduced atmosphere; and
  - heating said packaged implant while maintaining said oxygen reduced
  - 30 atmosphere for at least 48 hours at a temperature of about 37°C to about 70°C.
24. The method for producing an implant as set forth in claim 23 wherein the polymeric material is ultra high molecular weight polyethylene having a molecular weight between 400,000 and 10,000,000.

25. The method for producing an implant as set forth in claim 23 wherein said predetermined temperature is 50°C and said predetermined time is 144 hours.

26. The method as set forth in claim 19 wherein said oxygen reduced atmosphere has no more than 1% oxygen.

5 27. The method for producing an implant as set forth in claim 26 wherein said oxygen reduced atmosphere is made up of a gas selected from the group consisting of nitrogen, helium, argon, and neon and a combination thereof.

28. The method for producing an implant as set forth in claim 26 wherein said reduced oxygen atmosphere is produced by a vacuum of less than 3 inches of  
10 mercury.

29. The method as set forth in claim 23 wherein said heating step is performed in an inert atmosphere.

# INTERNATIONAL SEARCH REPORT

Inter. Application No

PCT/IB 94/00083

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 5 A61L27/00 A61L31/00 A61L29/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 376 503 (E.I. DU PONT DE NEMOURS AND CO.) 4 July 1990 cited in the application see claims & US,A,5 153 039 (IDEM) ---	1
A	EP,A,0 373 800 (E.I. DU PONT DE NEMOURS AND CO.) 20 June 1990 see examples 1-13 ---	1
A	EP,A,0 218 003 (NISSHO CORP.) 15 April 1987 cited in the application see the whole document & GB,A,2 180 815 (IDEM) ---	1
-/--		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

### \* Special categories of cited documents :

- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed

- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* "&" document member of the same patent family

Date of the actual completion of the international search

12 July 1994

Date of mailing of the international search report

26. 07. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

ESPINOSA, M



# INTERNATIONAL SEARCH REPORT

Inter. Application No  
PCT/IB 94/00083

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US,A,5 153 039 (JAY P. PORTER ET AL.) 6 October 1992 cited in the application see claims</p> <p>-----</p>	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int'l. Application No

PCT/IB 94/00083

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0376503	04-07-90	CA-A- 2004455 EP-A- 0449878 JP-T- 4502024 WO-A- 9006140 US-A- 5037928	02-06-90 09-10-91 09-04-92 14-06-90 06-08-91
US-A-5153039	06-10-92	NONE	
EP-A-0373800	20-06-90	CA-A- 2004454 EP-A- 0446300 JP-T- 4502028 WO-A- 9006139	02-06-90 18-09-91 09-04-92 14-06-90
EP-A-0218003	15-04-87	JP-B- 4070023 JP-A- 62074364 FR-A, B 2587977 GB-A, B 2180815 SE-C- 500074 SE-A- 8601776 US-A- 4813210	09-11-92 06-04-87 03-04-87 08-04-87 11-04-94 28-03-87 21-03-89
GB-A-2180815	08-04-87	JP-B- 4070023 JP-A- 62074364 EP-A, B 0218003 FR-A, B 2587977 SE-C- 500074 SE-A- 8601776 US-A- 4813210	09-11-92 06-04-87 15-04-87 03-04-87 11-04-94 28-03-87 21-03-89
US-A-5153039	06-10-92	NONE	

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**